



PROPERTIES		VALUES	UNIT	TEST METHOD
Tensile strength	MD	145	[N/mm ²]	ASTM-D-882
	TD	309		
Yield		91	[m ² /kg]	ASTM-D-882
Elongation at break	MD	170	[%]	ASTM-D-882
	TD	450		
Coefficient of friction		0,25	[-]	ASTM-D-1894 F/F
Gloss		200	[%]	ASTM-D-2457 60°
Thermal stability 190°C 5 min.	MD	4	[%]	-
	TD	2		
Haze		1,75	[%]	ASTM-D-1003
Gauge		12	[micron]	-
Unit weight		10,95	[g/m ²]	ASTM-D-882
UV stability		-	[DE]	-
Wetting tension		39	[dynes/cm]	ASTM-D-2578
Food contact approval		YES	[-]	-